

Amendments to the Specification:

In the Abstract:

Please replace the Abstract with the following amended Abstract

A soft polyurethane foam obtained by foaming a polyurethane raw material including a the phenolic antioxidant selected from 3,9-bis[2-(3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy)-1,1-dimethylethyl]-2,4,8,10-tetraoxapyro[5,5]undecane and/or 2,2'-thio-diethylene bis[3-(3,5-di-tert-butyl-4-hydroxyphenyl)propionate 3,9-bis(1,1-dimethyl-2-(3-(3-tert-butyl-4-hydroxy-5-methylphenyl)propionyloxy)ethyl)-2,4,8,10-tetraoxaspiro(5.5) undecane in an amount of 0.05 - 2.0 parts by weight, a benzotriazole type UV absorbing agent in an amount of 0.1 - 3.0 parts by weight, and a phosphorus type antioxidant in an amount of 0.5 - 6.0 parts by weight for 100 parts by weight of a polyol component. Color migration and discoloration of a soft polyurethane foam are prevented.